

Messrs.

Date:

## APPROVAL SHEET

Product Name : Ultra high Q/ Low ESR Multilayer Ceramic Chip  
Capacitors

Part No. : RF Series

Description : Size 01005 ~ 0805 , C0G(NPO) , 6.3Vdc to 500Vdc

PREPARED BY	APPROVED BY

信昌電子陶瓷股份有限公司

PROSPERITY DIELECTRICS CO., LTD.

桃園縣蘆竹鄉南山路二段 220-1 號 <http://www.pdc.com.tw>

Tel: 03-322-4471 ext: Fax: 03-322-5231 / 03-321-2215

Contact: \_\_\_\_\_ Mobile: \_\_\_\_\_

SPECIFICATION FOR  
ULTRA HIGH Q/LOW ESR MULTILAYER CERAMIC CHIP  
CAPACITORS

Part No. : RF Series

Description : Size 01005 ~ 0805 , C0G(NPO) , 6.3Vdc to 500Vdc

<u>DRAWN BY</u>	<u>CHECKED BY</u>	<u>APPROVED BY</u>
蕭敏珍	蔡永承	巫宏俊

## 1. INTRODUCTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

PDC RF series MLCC is used at high frequencies generally have a small temperature coefficient of capacitance, typical within the  $\pm 30\text{ppm}/^\circ\text{C}$  required for NP0 (C0G) classification and have excellent conductivity internal electrode. Thus, PDC RF series MLCC will be with the feature of low ESR and high Q characteristics.

## 2. FEATURES

- High Q and low ESR performance at high frequency.
- Ultra low capacitance to 0.1pF.
- Can offer high precision tolerance to  $\pm 0.05\text{pF}$ .
- Quality improvement of telephone calls for low power loss and better performance.

## 3. APPLICATIONS


- Telecommunication products & equipments: Mobile phone, WLAN, Base station.
- RF module: Power amplifier, VCO.
- Tuners.

## 4. HOW TO ORDER

<u>RF</u>	<u>21</u>	<u>N</u>	<u>101</u>	<u>J</u>	<u>251</u>	<u>C</u>	<u>I</u>
<u>Series</u>	<u>Size</u>	<u>Dielectric</u>	<u>Capacitance</u>	<u>Tolerance</u>	<u>Rated voltage</u>	<u>Termination</u>	<u>Packaging</u>
RF=Ultra High Q & Low ESR	02=01005(0402) 03=0201 (0603) 11=0505 (1414) 15=0402 (1005) 18=0603 (1608) 21=0805 (2012)	N=NP0 (C0G)	Two significant digits followed by no. of zeros. And R is in place of decimal point.  eg.: 0R5=0.5pF 1R0=1.0pF 100=10x10 <sup>0</sup> =10pF	A= $\pm 0.05\text{pF}$ B= $\pm 0.1\text{pF}$ C= $\pm 0.25\text{pF}$ D= $\pm 0.5\text{pF}$ F= $\pm 1\%$ G= $\pm 2\%$ J= $\pm 5\%$	Two significant digits followed by no. of zeros. And R is in place of decimal point.  6R3=6.3 VDC 100=10 VDC 250=25 VDC 500=50 VDC 101=100 VDC 251=250 VDC 501=500 VDC	C=Cu/Ni/Sn	T=7" reeled G= 13" reeled

## 5. EXTERNAL DIMENSIONS

Size Inch (mm)	L (mm)	W (mm)	T (mm)/Symbol	Remark	M <sub>B</sub> (mm)
01005 (0402)	0.40±0.02	0.20±0.02	0.20±0.02	V #	0.10±0.03
0201 (0603)	0.60±0.03	0.30±0.03	0.30±0.03	L #	0.15±0.05
0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	N #	0.25±0.05/-0.10
0603 (1608)	1.60±0.10	0.80±0.10	0.80±0.07	S	0.40±0.15
	1.60 +0.15/-0.10	0.80 +0.15/-0.10	0.50±0.10	H	
0805 (2012)	2.00±0.15	1.25±0.10	0.60±0.10	A	0.50±0.20
	2.00±0.20	1.25±0.20	0.85±0.10	T	
0505 (1414)	1.40±0.38/-0	1.40±0.38	1.15±0.15	J #	0.25±0.25/-0.13



## 6. GENERAL ELECTRICAL DATA

<b>Dielectric</b>	NP0
<b>Size</b>	01005, 0201, 0402, 0505, 0603, 0805
<b>Capacitance*</b>	0.1pF to 100pF
<b>Capacitance tolerance</b>	Cap≤5pF: A (±0.05pF), B (±0.1pF), C (±0.25pF) 5pF<Cap<10pF: B (±0.1pF), C (±0.25pF), D (±0.5pF) Cap≥10pF: F (±1%), G (±2%), J (±5%)
<b>Rated voltage (WVDC)</b>	6.3V, 10V, 25V, 50V, 100V, 200V, 250V, 500V
<b>Q*</b>	01005, 0201, 0402/25V~50V: Cap<30pF:Q≥400+20C; Cap≥30pF:Q≥1000 0402/100V~200V, 0603, 0805, 0505: Cap<30pF:Q≥800+20C; Cap≥30pF:Q≥1400
<b>Insulation resistance at U<sub>r</sub></b>	≥10GΩ or R <sub>x</sub> C≥100Ω·F whichever is smaller.
<b>Operating temperature</b>	-55 to +125°C
<b>Capacitance change</b>	±30ppm/°C; 0201Cap ≥22pF, ±60ppm/°C
<b>Termination</b>	Ni/Sn (lead-free termination)

\* Measured at the conditions of 25°C ambient temperature and 30~70% related humidity.

Apply 1.0±0.2V<sub>rms</sub>, 1.0MHz±10% for Cap≤1000pF and 1.0±0.2V<sub>rms</sub>, 1.0kHz±10% for Cap>1000pF.

## 7. CAPACITANCE RANGE

DIELECTRIC		NP0		Tolerance
SIZE		01005		
RATED VOLTAGE (VDC)		16	25	
Capacitance	0.2pF (0R2)	V	V	A, B
	0.3pF (0R3)	V	V	A, B
	0.4pF (0R4)	V	V	A, B
	0.5pF (0R5)	V	V	A, B, C
	0.6pF (0R6)	V	V	A, B, C
	0.7pF (0R7)	V	V	A, B, C
	0.8pF (0R8)	V	V	A, B, C
	0.9pF (0R9)	V	V	A, B, C
	1.0pF (1R0)	V	V	A, B, C
	1.2pF (1R2)	V	V	A, B, C
	1.5pF (1R5)	V	V	A, B, C
	1.8pF (1R8)	V	V	A, B, C
	2.0pF (2R0)	V	V	A, B, C
	2.2pF (2R2)	V	V	A, B, C
	2.7pF (2R7)	V	V	A, B, C
	3.0pF (3R0)	V	V	A, B, C
	3.3pF (3R3)	V	V	A, B, C
	3.9pF (3R9)	V	V	A, B, C
	4.0pF (4R0)	V	V	A, B, C
	4.7pF (4R7)	V	V	A, B, C
	5.0pF (5R0)	V	V	A, B, C
	5.6pF (5R6)	V	V	B, C, D
6.0pF (6R0)	V	V	B, C, D	
6.8pF (6R8)	V		B, C, D	
7.0pF (7R0)	V		B, C, D	
8.0pF (8R0)	V		B, C, D	
8.2pF (8R2)	V		B, C, D	
9.0pF (9R0)	V		B, C, D	
10pF (100)	V	V	C, D, G	
12pF (120)	V	V	J	
15pF (150)	V	V	J	
20pF (200)	V	V	J	
22pF (220)	V	V	J	

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

## 7. CAPACITANCE RANGE

DIELECTRIC		NPO								Tolerance
SIZE		0201				0402				
RATED VOLTAGE (VDC)		6.3	10	25	50	25	50	100	200	
Capacitance	0.1pF (0R1)	L	L	L	L	N	N	N	N	B
	0.2pF (0R2)	L	L	L	L	N	N	N	N	A, B
	0.3pF (0R3)	L	L	L	L	N	N	N	N	A, B
	0.4pF (0R4)	L	L	L	L	N	N	N	N	A, B
	0.5pF (0R5)	L	L	L	L	N	N	N	N	A, B, C
	0.6pF (0R6)	L	L	L	L	N	N	N	N	A, B, C
	0.7pF (0R7)	L	L	L	L	N	N	N	N	A, B, C
	0.8pF (0R8)	L	L	L	L	N	N	N	N	A, B, C
	0.9pF (0R9)	L	L	L	L	N	N	N	N	A, B, C
	1.0pF (1R0)	L	L	L	L	N	N	N	N	A, B, C
	1.1pF (1R1)	L	L	L	L	N	N	N	N	A, B, C
	1.2pF (1R2)	L	L	L	L	N	N	N	N	A, B, C
	1.3pF (1R3)	L	L	L	L	N	N	N	N	A, B, C
	1.4pF (1R4)	L	L	L	L	N	N	N	N	A, B, C
	1.5pF (1R5)	L	L	L	L	N	N	N	N	A, B, C
	1.6pF (1R6)	L	L	L	L	N	N	N	N	A, B, C
	1.7pF (1R7)	L	L	L	L	N	N	N	N	A, B, C
	1.8pF (1R8)	L	L	L	L	N	N	N	N	A, B, C
	1.9pF (1R9)	L	L	L	L	N	N	N	N	A, B, C
	2.0pF (2R0)	L	L	L	L	N	N	N	N	A, B, C
	2.1pF (2R1)	L	L	L	L	N	N	N	N	A, B, C
	2.2pF (2R2)	L	L	L	L	N	N	N	N	A, B, C
	2.3pF (2R3)	L	L	L	L	N	N	N	N	A, B, C
	2.4pF (2R4)	L	L	L	L	N	N	N	N	A, B, C
	2.5pF (2R5)	L	L	L	L	N	N	N	N	A, B, C
	2.6pF (2R6)	L	L	L	L	N	N	N	N	A, B, C
	2.7pF (2R7)	L	L	L	L	N	N	N	N	A, B, C
	2.8pF (2R8)	L	L	L	L	N	N	N	N	A, B, C
	2.9pF (2R9)	L	L	L	L	N	N	N	N	A, B, C
	3.0pF (3R0)	L	L	L	L	N	N	N	N	A, B, C
	3.1pF (3R1)	L	L	L	L	N	N	N	N	A, B, C
	3.2pF (3R2)	L	L	L	L	N	N	N	N	A, B, C
	3.3pF (3R3)	L	L	L	L	N	N	N	N	A, B, C
	3.4pF (3R4)	L	L	L	L	N	N	N	N	A, B, C
	3.5pF (3R5)	L	L	L	L	N	N	N	N	A, B, C
	3.6pF (3R6)	L	L	L	L	N	N	N	N	A, B, C
	3.7pF (3R7)	L	L	L	L	N	N	N	N	A, B, C
	3.8pF (3R8)	L	L	L	L	N	N	N	N	A, B, C
	3.9pF (3R9)	L	L	L	L	N	N	N	N	A, B, C
	4.0pF (4R0)	L	L	L	L	N	N	N	N	A, B, C
	4.1pF (4R1)	L	L	L	L	N	N	N	N	A, B, C
	4.2pF (4R2)	L	L	L	L	N	N	N	N	A, B, C
	4.3pF (4R3)	L	L	L	L	N	N	N	N	A, B, C
	4.4pF (4R4)	L	L	L	L	N	N	N	N	A, B, C
	4.5pF (4R5)	L	L	L	L	N	N	N	N	A, B, C
	4.6pF (4R6)	L	L	L	L	N	N	N	N	A, B, C
	4.7pF (4R7)	L	L	L	L	N	N	N	N	A, B, C
	4.8pF (4R8)	L	L	L	L	N	N	N	N	A, B, C
	4.9pF (4R9)	L	L	L	L	N	N	N	N	A, B, C
	5.0pF (5R0)	L	L	L	L	N	N	N	N	A, B, C
	5.1pF (5R1)	L	L	L	L	N	N	N	N	B, C, D
	5.2pF (5R2)	L	L	L	L	N	N	N	N	B, C, D
	5.3pF (5R3)	L	L	L	L	N	N	N	N	B, C, D
	5.4pF (5R4)	L	L	L	L	N	N	N	N	B, C, D
	5.5pF (5R5)	L	L	L	L	N	N	N	N	B, C, D
	5.6pF (5R6)	L	L	L	L	N	N	N	N	B, C, D
	5.7pF (5R7)	L	L	L	L	N	N	N	N	B, C, D
	5.8pF (5R8)	L	L	L	L	N	N	N	N	B, C, D
	5.9pF (5R9)	L	L	L	L	N	N	N	N	B, C, D
	6.0pF (6R0)	L	L	L	L	N	N	N	N	B, C, D

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact PDC local representative.

## 7. CAPACITANCE RANGE

DIELECTRIC		NPO								Tolerance
SIZE		0201				0402				
RATED VOLTAGE (VDC)		6.3	10	25	50	25	50	100	200	
Capacitance	6.1pF (6R1)	L	L	L	L	N	N	N	N	B, C, D
	6.2pF (6R2)	L	L	L	L	N	N	N	N	B, C, D
	6.3pF (6R3)	L	L	L	L	N	N	N	N	B, C, D
	6.4pF (6R4)	L	L	L	L	N	N	N	N	B, C, D
	6.5pF (6R5)	L	L	L	L	N	N	N	N	B, C, D
	6.6pF (6R6)	L	L	L	L	N	N	N	N	B, C, D
	6.7pF (6R7)	L	L	L	L	N	N	N	N	B, C, D
	6.8pF (6R8)	L	L	L	L	N	N	N	N	B, C, D
	6.9pF (6R9)	L	L	L	L	N	N	N	N	B, C, D
	7.0pF (7R0)	L	L	L	L	N	N	N	N	B, C, D
	7.1pF (7R1)	L	L	L	L	N	N	N	N	B, C, D
	7.2pF (7R2)	L	L	L	L	N	N	N	N	B, C, D
	7.3pF (7R3)	L	L	L	L	N	N	N	N	B, C, D
	7.4pF (7R4)	L	L	L	L	N	N	N	N	B, C, D
	7.5pF (7R5)	L	L	L	L	N	N	N	N	B, C, D
	7.6pF (7R6)	L	L	L	L	N	N	N	N	B, C, D
	7.7pF (7R7)	L	L	L	L	N	N	N	N	B, C, D
	7.8pF (7R8)	L	L	L	L	N	N	N	N	B, C, D
	7.9pF (7R9)	L	L	L	L	N	N	N	N	B, C, D
	8.0pF (8R0)	L	L	L	L	N	N	N	N	B, C, D
	8.1pF (8R1)	L	L	L	L	N	N	N	N	B, C, D
	8.2pF (8R2)	L	L	L	L	N	N	N	N	B, C, D
	8.3pF (8R3)	L	L	L	L	N	N	N	N	B, C, D
	8.4pF (8R4)	L	L	L	L	N	N	N	N	B, C, D
	8.5pF (8R5)	L	L	L	L	N	N	N	N	B, C, D
	8.6pF (8R6)	L	L	L	L	N	N	N	N	B, C, D
	8.7pF (8R7)	L	L	L	L	N	N	N	N	B, C, D
	8.8pF (8R8)	L	L	L	L	N	N	N	N	B, C, D
	8.9pF (8R9)	L	L	L	L	N	N	N	N	B, C, D
	9.0pF (9R0)	L	L	L	L	N	N	N	N	B, C, D
	9.1pF (9R1)	L	L	L	L	N	N	N	N	B, C, D
	9.2pF (9R2)	L	L	L	L	N	N	N	N	B, C, D
	9.3pF (9R3)	L	L	L	L	N	N	N	N	B, C, D
	9.4pF (9R4)	L	L	L	L	N	N	N	N	B, C, D
	9.5pF (9R5)	L	L	L	L	N	N	N	N	B, C, D
	9.6pF (9R6)	L	L	L	L	N	N	N	N	B, C, D
	9.7pF (9R7)	L	L	L	L	N	N	N	N	B, C, D
	9.8pF (9R8)	L	L	L	L	N	N	N	N	B, C, D
	9.9pF (9R9)	L	L	L	L	N	N	N	N	B, C, D
	10pF (100)	L	L	L	L	N	N	N	N	F, G, J
11pF (110)	L	L	L	L	N	N	N	N	F, G, J	
12pF (120)	L	L	L	L	N	N	N	N	F, G, J	
13pF (130)	L	L	L	L	N	N	N	N	F, G, J	
15pF (150)	L	L	L	L	N	N	N	N	F, G, J	
16pF (160)	L	L	L	L	N	N	N	N	F, G, J	
18pF (180)	L	L	L	L	N	N	N	N	F, G, J	
20pF (200)	L	L	L	L	N	N	N	N	F, G, J	
22pF (220)	L	L	L	L	N	N	N	N	F, G, J	
24pF (240)	L	L	L	L	N	N	N	N	F, G, J	
27pF (270)	L	L	L	L	N	N	N	N	F, G, J	
30pF (300)	L	L	L	L	N	N	N	N	F, G, J	
33pF (330)	L	L	L	L	N	N	N	N	F, G, J	
36pF (360)					N	N	N	N	F, G, J	
39pF (390)					N	N	N	N	F, G, J	
43pF (430)					N	N	N	N	F, G, J	
47pF (470)					N	N	N	N	F, G, J	
56pF (560)					N	N	N	N	F, G, J	
68pF (680)					N	N	N	N	F, G, J	
82pF (820)					N	N	N	N	F, G, J	
100pF (101)					N	N	N	N	F, G, J	

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact PDC local representative.

## 7. CAPACITANCE RANGE

DIELECTRIC		NPO							Tolerance	
SIZE	0505	0603			0805					
RATED VOLTAGE (VDC)	250	50	100	250	50	100	250	500		
Capacitance	0.1pF (0R1)		H	H	H					A, B
	0.2pF (0R2)		H	H	H	A	A	A	A	A, B
	0.3pF (0R3)		S	S	S	T	T	T	T	A, B
	0.4pF (0R4)	J	S	S	S	T	T	T	T	A, B
	0.5pF (0R5)	J	S	S	S	T	T	T	T	A, B, C
	0.6pF (0R6)	J	S	S	S	T	T	T	T	A, B, C
	0.7pF (0R7)	J	S	S	S	T	T	T	T	A, B, C
	0.8pF (0R8)	J	S	S	S	T	T	T	T	A, B, C
	0.9pF (0R9)	J	S	S	S	T	T	T	T	A, B, C
	1.0pF (1R0)	J	S	S	S	T	T	T	T	A, B, C
	1.1pF (1R1)	J	S	S	S	T	T	T	T	A, B, C
	1.2pF (1R2)	J	S	S	S	T	T	T	T	A, B, C
	1.3pF (1R3)	J	S	S	S	T	T	T	T	A, B, C
	1.4pF (1R4)	J	S	S	S	T	T	T	T	A, B, C
	1.5pF (1R5)	J	S	S	S	T	T	T	T	A, B, C
	1.6pF (1R6)	J	S	S	S	T	T	T	T	A, B, C
	1.7pF (1R7)	J	S	S	S	T	T	T	T	A, B, C
	1.8pF (1R8)	J	S	S	S	T	T	T	T	A, B, C
	1.9pF (1R9)	J	S	S	S	T	T	T	T	A, B, C
	2.0pF (2R0)	J	S	S	S	T	T	T	T	A, B, C
	2.1pF (2R1)	J	S	S	S	T	T	T	T	A, B, C
	2.2pF (2R2)	J	S	S	S	T	T	T	T	A, B, C
	2.3pF (2R3)	J	S	S	S	T	T	T	T	A, B, C
	2.4pF (2R4)	J	S	S	S	T	T	T	T	A, B, C
	2.5pF (2R5)	J	S	S	S	T	T	T	T	A, B, C
	2.6pF (2R6)	J	S	S	S	T	T	T	T	A, B, C
	2.7pF (2R7)	J	S	S	S	T	T	T	T	A, B, C
	2.8pF (2R8)	J	S	S	S	T	T	T	T	A, B, C
	2.9pF (2R9)	J	S	S	S	T	T	T	T	A, B, C
	3.0pF (3R0)	J	S	S	S	T	T	T	T	A, B, C
	3.1pF (3R1)	J	S	S	S	T	T	T	T	A, B, C
	3.2pF (3R2)	J	S	S	S	T	T	T	T	A, B, C
	3.3pF (3R3)	J	S	S	S	T	T	T	T	A, B, C
	3.4pF (3R4)	J	S	S	S	T	T	T	T	A, B, C
	3.5pF (3R5)	J	S	S	S	T	T	T	T	A, B, C
	3.6pF (3R6)	J	S	S	S	T	T	T	T	A, B, C
	3.7pF (3R7)	J	S	S	S	T	T	T	T	A, B, C
	3.8pF (3R8)	J	S	S	S	T	T	T	T	A, B, C
	3.9pF (3R9)	J	S	S	S	T	T	T	T	A, B, C
	4.0pF (4R0)	J	S	S	S	T	T	T	T	A, B, C
	4.1pF (4R1)	J	S	S	S	T	T	T	T	A, B, C
	4.2pF (4R2)	J	S	S	S	T	T	T	T	A, B, C
	4.3pF (4R3)	J	S	S	S	T	T	T	T	A, B, C
	4.4pF (4R4)	J	S	S	S	T	T	T	T	A, B, C
	4.5pF (4R5)	J	S	S	S	T	T	T	T	A, B, C
	4.6pF (4R6)	J	S	S	S	T	T	T	T	A, B, C
	4.7pF (4R7)	J	S	S	S	T	T	T	T	A, B, C
	4.8pF (4R8)	J	S	S	S	T	T	T	T	A, B, C
	4.9pF (4R9)	J	S	S	S	T	T	T	T	A, B, C
	5.0pF (5R0)	J	S	S	S	T	T	T	T	A, B, C
	5.1pF (5R1)	J	S	S	S	T	T	T	T	B, C, D
	5.2pF (5R2)	J	S	S	S	T	T	T	T	B, C, D
	5.3pF (5R3)	J	S	S	S	T	T	T	T	B, C, D
	5.4pF (5R4)	J	S	S	S	T	T	T	T	B, C, D
	5.5pF (5R5)	J	S	S	S	T	T	T	T	B, C, D
	5.6pF (5R6)	J	S	S	S	T	T	T	T	B, C, D
	5.7pF (5R7)	J	S	S	S	T	T	T	T	B, C, D
	5.8pF (5R8)	J	S	S	S	T	T	T	T	B, C, D
	5.9pF (5R9)	J	S	S	S	T	T	T	T	B, C, D
	6.0pF (6R0)	J	S	S	S	T	T	T	T	B, C, D

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact PDC local representative.



## 7. CAPACITANCE RANGE

DIELECTRIC		NP0							Tolerance	
SIZE	0505	0603			0805					
RATED VOLTAGE (VDC)	250	50	100	250	50	100	250	500		
Capacitance	6.1pF (6R1)	J	S	S	S	T	T	T	T	B, C, D
	6.2pF (6R2)	J	S	S	S	T	T	T	T	B, C, D
	6.3pF (6R3)	J	S	S	S	T	T	T	T	B, C, D
	6.4pF (6R4)	J	S	S	S	T	T	T	T	B, C, D
	6.5pF (6R5)	J	S	S	S	T	T	T	T	B, C, D
	6.6pF (6R6)	J	S	S	S	T	T	T	T	B, C, D
	6.7pF (6R7)	J	S	S	S	T	T	T	T	B, C, D
	6.8pF (6R8)	J	S	S	S	T	T	T	T	B, C, D
	6.9pF (6R9)	J	S	S	S	T	T	T	T	B, C, D
	7.0pF (7R0)	J	S	S	S	T	T	T	T	B, C, D
	7.1pF (7R1)	J	S	S	S	T	T	T	T	B, C, D
	7.2pF (7R2)	J	S	S	S	T	T	T	T	B, C, D
	7.3pF (7R3)	J	S	S	S	T	T	T	T	B, C, D
	7.4pF (7R4)	J	S	S	S	T	T	T	T	B, C, D
	7.5pF (7R5)	J	S	S	S	T	T	T	T	B, C, D
	7.6pF (7R6)	J	S	S	S	T	T	T	T	B, C, D
	7.7pF (7R7)	J	S	S	S	T	T	T	T	B, C, D
	7.8pF (7R8)	J	S	S	S	T	T	T	T	B, C, D
	7.9pF (7R9)	J	S	S	S	T	T	T	T	B, C, D
	8.0pF (8R0)	J	S	S	S	T	T	T	T	B, C, D
	8.1pF (8R1)	J	S	S	S	T	T	T	T	B, C, D
	8.2pF (8R2)	J	S	S	S	T	T	T	T	B, C, D
	8.3pF (8R3)	J	S	S	S	T	T	T	T	B, C, D
	8.4pF (8R4)	J	S	S	S	T	T	T	T	B, C, D
	8.5pF (8R5)	J	S	S	S	T	T	T	T	B, C, D
	8.6pF (8R6)	J	S	S	S	T	T	T	T	B, C, D
	8.7pF (8R7)	J	S	S	S	T	T	T	T	B, C, D
	8.8pF (8R8)	J	S	S	S	T	T	T	T	B, C, D
	8.9pF (8R9)	J	S	S	S	T	T	T	T	B, C, D
	9.0pF (9R0)	J	S	S	S	T	T	T	T	B, C, D
	9.1pF (9R1)	J	S	S	S	T	T	T	T	B, C, D
	9.2pF (9R2)	J	S	S	S	T	T	T	T	B, C, D
	9.3pF (9R3)	J	S	S	S	T	T	T	T	B, C, D
	9.4pF (9R4)	J	S	S	S	T	T	T	T	B, C, D
	9.5pF (9R5)	J	S	S	S	T	T	T	T	B, C, D
	9.6pF (9R6)	J	S	S	S	T	T	T	T	B, C, D
	9.7pF (9R7)	J	S	S	S	T	T	T	T	B, C, D
	9.8pF (9R8)	J	S	S	S	T	T	T	T	B, C, D
	9.9pF (9R9)	J	S	S	S	T	T	T	T	B, C, D
	10pF (100)	J	S	S	S	T	T	T	T	F, G, J
11pF (110)	J	S	S	S	T	T	T	T	F, G, J	
12pF (120)	J	S	S	S	T	T	T	T	F, G, J	
13pF (130)	J	S	S	S	T	T	T	T	F, G, J	
15pF (150)	J	S	S	S	T	T	T	T	F, G, J	
16pF (160)	J	S	S	S	T	T	T	T	F, G, J	
18pF (180)	J	S	S	S	T	T	T	T	F, G, J	
20pF (200)	J	S	S	S	T	T	T	T	F, G, J	
22pF (220)	J	S	S	S	T	T	T	T	F, G, J	
24pF (240)	J	S	S	S	T	T	T	T	F, G, J	
27pF (270)	J	S	S	S	T	T	T	T	F, G, J	
30pF (300)	J	S	S	S	T	T	T	T	F, G, J	
33pF (330)	J	S	S	S	T	T	T	T	F, G, J	
36pF (360)	J	S	S	S	T	T	T	T	F, G, J	
39pF (390)	J	S	S	S	T	T	T	T	F, G, J	
43pF (430)	J	S	S	S	T	T	T	T	F, G, J	
47pF (470)	J	S	S	S	T	T	T	T	F, G, J	
56pF (560)	J	S	S	S	T	T	T	T	F, G, J	
68pF (680)	J	S	S	S	T	T	T	T	F, G, J	
75pF (750)	J	S	S	S	T	T	T	T	F, G, J	
82pF (820)	J	S	S	S	T	T	T	T	F, G, J	
100pF (101)	J	S	S	S	T	T	T	T	F, G, J	

1. The letter in cell is expressed the symbol of product thickness.







2. For more information about products with special capacitance or other data, please contact PDC local representative.

## 8. PACKAGING DIMENSION AND QUANTITY







Size	Thickness (mm)/Symbol		Paper tape	
			7" reel	13" reel
01005 (0402)	0.20±0.02	V	20,000	-
0201 (0603)	0.30±0.03	L	15,000	70,000
0402 (1005)	0.50±0.05	N	10,000	50,000
0603 (1608)	0.80±0.07	S	4,000	15,000
	0.50±0.10	H	4,000	-
0805 (2012)	0.60±0.10	A	4,000	15,000
	0.85±0.10	T	4,000	15,000
Size	Thickness (mm)/Symbol		Plastic tape	
			7" reel	13" reel
0505 (1414)	1.15±0.15	J	3,000	-

Unit: pieces





## 9. ELECTRICAL CHARACTERISTICS



## 9. ELECTRICAL CHARACTERISTICS(Con.)



## 9. ELECTRICAL CHARACTERISTICS(Con.)



## 10. RELIABILITY TEST CONDITIONS AND REQUIREMENTS




No.	Item	Test Conditions	Requirements
1.	Visual and Mechanical	---	* No remarkable defect. * Dimensions to conform to individual specification sheet.
2.	Capacitance	1.0±0.2Vrms, 1MHz±10%	* Shall not exceed the limits given in the detailed spec.
3.	Q/ D.F. (Dissipation Factor)	At 25°C ambient temperature.	* 01005, 0201, 0402/25V~50V: Cap<30pF,Q≥400+20C;Cap≥30pF, Q≥1000 *0402/100V~200V, 0603, 0805, 0505: Cap<30pF:Q≥800+20C;Cap≥30pF:Q≥1400
4.	Dielectric Strength	*To apply voltage: ≤ 100V : 250% of rated voltage. 200V ~ 300V : 200% of rated voltage. 500V ~ 999V : 150% of rated voltage. 1000V ~ 3000V : 120% of rated voltage. 4000V : 110% of rated voltage. *Duration: 1 to 5 sec. *Charge & discharge current less than 50mA.	* No evidence of damage or flash over during test.
5.	Insulation Resistance	≤100V : To apply rated voltage for max. 120 sec. ≥200V :To apply rated voltage (500V max.) for 60 sec.	≥10GΩ or RxC≥100Ω-F whichever is smaller
6.	Temperature Coefficient	With no electrical load. Operating temperature: -55~125°C at 25°C	* Capacitance change: within ±30ppm/°C; 0201Cap≥22pF, within ±60ppm/°C
7.	Adhesive Strength of Termination	* Pressurizing force : 01005: 1N 0201: 2N 0402 to 0603: 5N >0603: 10N * Test time: 10±1 sec.	* No remarkable damage or removal of the terminations.
8.	Vibration Resistance	* Vibration frequency: 10~55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.) *Cap./DF(Q) Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	* No remarkable damage. * Cap change and Q/D.F.: To meet initial spec.
9.	Solderability	* Solder temperature: 235±5°C * Dipping time: 2±0.5 sec.	95% min. coverage of all metalized area.
10.	Bending Test	* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec. * Measurement to be made after keeping at room temp. for 24±2 hrs.	* No remarkable damage. * Cap change: within ±5.0% or ±0.5pF whichever is larger. (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)
11.	Resistance to Soldering Heat	* Solder temperature: 260±5°C * Dipping time: 10±1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. *Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	* No remarkable damage. * Cap change: within ±2.5% or ±0.25pF whichever is larger. * Q/D.F., I.R. and dielectric strength: To meet initial requirements. * 25% max. leaching on each edge.

## 10. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																												
12.	Temperature Cycle	<p>* Conduct the five cycles according to the temperatures and time.</p> <table border="1"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> <p>* Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.</p>	Step	Temp. (°C)	Time (min.)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	<p>No remarkable damage.</p> <p>Cap change : within ±2.5% or ±0.25pF whichever is larger.</p> <p>* Q/D.F., I.R. and dielectric strength: To meet initial requirements.</p>													
Step	Temp. (°C)	Time (min.)																													
1	Min. operating temp. +0/-3	30±3																													
2	Room temp.	2~3																													
3	Max. operating temp. +3/-0	30±3																													
4	Room temp.	2~3																													
13.	Humidity (Damp Heat) Steady State	<p>* Test temp.: 40±2°C</p> <p>* Humidity: 90~95% RH</p> <p>* Test time: 500+24/-0hrs.</p> <p>* Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.</p>	<p>* No remarkable damage.</p> <p>* Cap change: within ±5.0% or ±0.5pF whichever is larger.</p> <p>* Q/D.F. value: Cap≥30pF, Q≥350; 10pF≤Cap&lt;30pF, Q≥275+2.5C Cap&lt;10pF; Q≥200+10C</p> <p>* I.R.: ≥1GΩ.</p>																												
14.	Humidity (Damp Heat) Load	<p>* Test temp.: 40±2°C</p> <p>* Humidity: 90~95%RH</p> <p>* Test time: 500+24/-0 hrs.</p> <p>* To apply voltage : rated voltage (MAX. 500V)</p> <p>* Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.</p>	<p>* No remarkable damage.</p> <p>* Cap change: within ±7.5% or ±0.75pF whichever is larger.</p> <p>* Q/D.F. value: Cap≥30pF, Q≥200; Cap&lt;30pF, Q≥100+10/3C</p> <p>* I.R.: ≥500MΩ.</p>																												
15.	High Temperature Load (Endurance)	<p>* Test temp.: 125±3°C</p> <p>* To apply voltage: (1) 10V ≤ Ur &lt; 500V: 200% of rated voltage. (2) ≤ 6.3V or 500V: 150% of rated voltage. (3) Ur ≥ 630V: 120% of rated voltage.</p> <p>* Test time: 1000+24/-0 hrs.</p> <p>* Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.</p>	<p>* No remarkable damage.</p> <p>* Cap change: within ±3.0% or ±0.3pF whichever is larger.</p> <p>* Q/D.F. value: Cap≥30pF, Q≥350 10pF≤Cap&lt;30pF, Q≥275+2.5C Cap&lt;10pF, Q≥200+10C</p> <p>* I.R.: ≥1GΩ.</p>																												
16.	ESR	<p>The ESR should be measured at room temperature and tested at frequency 1±0.1 GHz.</p>	<table border="1"> <thead> <tr> <th>01005</th> <th>0505</th> </tr> </thead> <tbody> <tr> <td>0.2pF≤Cap≤1pF:&lt; 700mΩ/pF</td> <td>0.4pF≤Cap&lt;1.0pF: &lt; 1500mΩ</td> </tr> <tr> <td>1pF&lt;Cap≤2pF:&lt; 600mΩ</td> <td>1.0pF≤Cap&lt;10pF: &lt; 250mΩ</td> </tr> <tr> <td>2pF&lt;Cap≤5pF:&lt; 500mΩ</td> <td>10pF≤Cap≤100pF: &lt; 200mΩ</td> </tr> <tr> <td>5pF&lt;Cap≤10pF:&lt; 300mΩ</td> <td></td> </tr> <tr> <td>10pF&lt;Cap≤22pF:&lt; 350mΩ</td> <td></td> </tr> <tr> <th>0201</th> <th>0402</th> </tr> <tr> <td>0.1pF≤Cap≤1pF:&lt; 350mΩ/pF</td> <td>0.1pF≤Cap≤1pF:&lt; 350mΩ/pF</td> </tr> <tr> <td>1pF&lt;Cap≤5pF:&lt; 300mΩ</td> <td>1pF&lt;Cap≤5pF:&lt; 300mΩ</td> </tr> <tr> <td>5pF&lt;Cap≤22pF:&lt; 250mΩ</td> <td>5pF&lt;Cap≤100pF:&lt; 250mΩ</td> </tr> <tr> <th>0603</th> <th>0805</th> </tr> <tr> <td>0.3pF≤Cap≤1pF:&lt; 1500mΩ</td> <td>0.3pF≤Cap≤1pF: &lt; 1500mΩ</td> </tr> <tr> <td>1pF&lt;Cap≤10pF:&lt; 250mΩ</td> <td>1pF&lt;Cap≤10pF: &lt; 250mΩ</td> </tr> <tr> <td>10pF&lt;Cap≤100pF:&lt; 200mΩ</td> <td>Cap&gt;10pF: &lt; 200mΩ</td> </tr> </tbody> </table> <p>0201, 22pF≤Cap≤33pF: &lt; 300mΩ</p>	01005	0505	0.2pF≤Cap≤1pF:< 700mΩ/pF	0.4pF≤Cap<1.0pF: < 1500mΩ	1pF<Cap≤2pF:< 600mΩ	1.0pF≤Cap<10pF: < 250mΩ	2pF<Cap≤5pF:< 500mΩ	10pF≤Cap≤100pF: < 200mΩ	5pF<Cap≤10pF:< 300mΩ		10pF<Cap≤22pF:< 350mΩ		0201	0402	0.1pF≤Cap≤1pF:< 350mΩ/pF	0.1pF≤Cap≤1pF:< 350mΩ/pF	1pF<Cap≤5pF:< 300mΩ	1pF<Cap≤5pF:< 300mΩ	5pF<Cap≤22pF:< 250mΩ	5pF<Cap≤100pF:< 250mΩ	0603	0805	0.3pF≤Cap≤1pF:< 1500mΩ	0.3pF≤Cap≤1pF: < 1500mΩ	1pF<Cap≤10pF:< 250mΩ	1pF<Cap≤10pF: < 250mΩ	10pF<Cap≤100pF:< 200mΩ	Cap>10pF: < 200mΩ
01005	0505																														
0.2pF≤Cap≤1pF:< 700mΩ/pF	0.4pF≤Cap<1.0pF: < 1500mΩ																														
1pF<Cap≤2pF:< 600mΩ	1.0pF≤Cap<10pF: < 250mΩ																														
2pF<Cap≤5pF:< 500mΩ	10pF≤Cap≤100pF: < 200mΩ																														
5pF<Cap≤10pF:< 300mΩ																															
10pF<Cap≤22pF:< 350mΩ																															
0201	0402																														
0.1pF≤Cap≤1pF:< 350mΩ/pF	0.1pF≤Cap≤1pF:< 350mΩ/pF																														
1pF<Cap≤5pF:< 300mΩ	1pF<Cap≤5pF:< 300mΩ																														
5pF<Cap≤22pF:< 250mΩ	5pF<Cap≤100pF:< 250mΩ																														
0603	0805																														
0.3pF≤Cap≤1pF:< 1500mΩ	0.3pF≤Cap≤1pF: < 1500mΩ																														
1pF<Cap≤10pF:< 250mΩ	1pF<Cap≤10pF: < 250mΩ																														
10pF<Cap≤100pF:< 200mΩ	Cap>10pF: < 200mΩ																														
		<p>The ESR should be measured at room temperature and tested at frequency 500±50 MHz.</p>																													

## 11. APPENDIXES

### ■ Tape & reel dimensions



Size	01005	0201	0402	0505	0603	0805
<b>Thickness</b>	<b>V</b>	<b>L</b>	<b>N</b>	<b>J</b>	<b>S</b>	<b>T</b>
<b>A<sub>0</sub></b>	0.25 +/-0.05	0.39 +/-0.07	0.70 +/-0.2	<1.90	1.05 +/-0.30	1.50 +/-0.20
<b>B<sub>0</sub></b>	0.45 +/-0.05	0.69 +/-0.07	1.20 +/-0.2	<1.90	1.80 +/-0.30	2.30 +/-0.20
<b>T</b>	≤ 0.50	≤ 0.50	≤ 0.80	0.23±0.10	≤ 1.20	≤ 1.30
<b>K<sub>0</sub></b>	-	-	-	<1.50	-	-
<b>W</b>	8.00 +/-0.10	8.00 +/-0.10	8.00 +/-0.10	8.00 +/-0.20	8.00 +/-0.10	8.00 +/-0.10
<b>P<sub>0</sub></b>	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10
<b>10xP<sub>0</sub></b>	40.00 +/-0.10	40.00 +/-0.10	40.00 +/-0.10	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20
<b>P<sub>1</sub></b>	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10
<b>P<sub>2</sub></b>	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05
<b>D<sub>0</sub></b>	1.55 +/-0.05	1.55 +/-0.05	1.55 +/-0.05	1.55 +/-0.05	1.55 +/-0.05	1.55 +/-0.05
<b>D<sub>1</sub></b>	-	-	-	1.00±0.10	-	-
<b>E</b>	1.75 +/-0.05	1.75 +/-0.05	1.75 +/-0.05	1.75 +/-0.05	1.75 +/-0.05	1.75 +/-0.05
<b>F</b>	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05

Size	01005, 0201, 0402, 0505, 0603, 0805	
<b>Reel size</b>	7"	13"
<b>C</b>	13.0+0.5/-0.2	13.0+0.5/-0.2
<b>W<sub>1</sub></b>	8.4+1.5/-0	8.4+1.5/-0
<b>A</b>	178.0±1.0	330.0±1.0
<b>N</b>	60.0+1.0/-0	100±1.0



■ **Constructions**

No.	Name	NPO	
①	Ceramic material	BaTiO <sub>3</sub> based	
②	Inner electrode	Cu	
③	Termination	Inner layer	Cu
④		Middle layer	Ni
⑤		Outer layer	Sn (Matt)




Fig. 21 The construction of MLCC

■ **Storage and handling conditions**

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70%. related humidity conditions.
- (2) The product is recommended to be used within one year after shipment. Check solderability in case of shelf life extension is needed.

Cautions:

- a. The corrosive gas reacts on the terminal electrodes of capacitors, and results in the poor solderability. Do not store the capacitors in the ambience of corrosive gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammonia gas etc.)
- b. In corrosive atmosphere, solderability might be degraded, and silver migration might occur to cause low reliability.
- c. Due to the dewing by rapid humidity change, or the photochemical change of the terminal electrode by direct sunlight, the solderability and electrical performance may deteriorate. Do not store capacitors under direct sunlight or dewing condition. To store products on the shelf and avoid exposure to moisture.

■ **Recommended soldering conditions**

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N<sub>2</sub> within oven are recommended.




Fig. 22 Recommended reflow soldering profile for SMT process with SnAgCu series solder paste.




Fig. 23 Recommended wave soldering profile for SMT process with SnAgCu series solder.